



Protecto-Ezeflor PU

Polyurethane Flooring System

PRODUCT DATASHEET

► Description:

Protecto-Ezeflor PU flooring systems are exceptionally hard wearing floor toppings with outstanding adhesion, chemical resistance, elasticity and flexural strength. They provide a long lasting, non-dusting, seamless surface which is easy to clean and maintain. Protecto-Ezeflor PU levels out holes and imperfections in the floor which facilitates movements of forklifts, pallet trucks and trolleys and also prevents further deterioration of the substrate.

► Salient Features:

- High abrasion resistance
- Excellent resistance to acids, alkalis, oils and chemicals
- Good adhesion to substrate
- High elasticity and flexural strength
- Easy application and maintenance
- Anti-fungal and anti-bacterial
- Dust free and anti-skid
- Fast curing
- Available in wide variety of colours



► Selection:

Protecto-Ezeflor PU flooring systems can be tailor made to suit the requirements of the customer. The choice of system and thickness of the floor will depend on various factors such as load, type of traffic, chemical resistance, safety requirements, operating temperature, aesthetics and economics.



► Surface Preparation:

The surface on which the floor coating is to be applied should be freed from all traces of dirt, grease and impurities. Commonly used surface preparation techniques include dust-free sand/grit blasting, high pressure power washing, flame blasting, concrete scarifying, wet scouring, wire brushing, etc.

Allow the surface to be totally dry before application. On metallic surfaces, remove all traces of rust to conform to Sa 2.5 on the Swedish de-rusting scale.

► Application:

Primer Coat

The components of the Primer coat (**PR-100A and PR-100B**) are mixed thoroughly in 2:1 ratio by weight and applied over the clean surface either by brush, trowel or lamb's wool roller. Use 150 grams/ sq. m to obtain a thickness of 125 microns. Apply the next coat over the Primer coat after 5 hours but not later than 48 hours.

Second Coat

For a *self leveling* second coat, mix **SL-200 A with SL-200B** in the specified ratio and spread over the surface using a saw toothed trowel. The mixture is poured in strips over the surface and then spread evenly with the trowel. Marks left by the trowel are eliminated by going over the trowelled material with a spiked plastic roller.

The desired thickness per coat is obtained by controlling the quantity of material that is spread per unit area. To obtain a 1 mm thickness of the self leveling coat, spread 1.1 kg of mixture over an area of 1 sq. m.

Third Coat

A third and final coating may be applied over the second coat only if a higher thickness is required. It is a repeat of the second coat. This coat is usually applied over the second coat after 5 hours but not later than 24 hours. Though light walking over the floor coating is permissible after 24 hours, it is advisable to wait for 3-4 days before full traffic is allowed to move over it.

► Uses:

Protecto-Ezeflor PU can be used in a wide range of commercial and industrial locations such as:

- Food & beverage factories
- Engineering workshops
- Kitchens and bathrooms
- Watch factories
- Power plants
- Electronic plant
- Textile and paper mills
- Chemical plants
- Restaurants and canteens
- Pharmaceutical plants
- Tobacco processing factories
- Metal working facilities

► Storage and Precautions:

Protecto-Ezeflor PU components should be stored in a cool and dry area. They can be stored for 9 months in their original un-opened container. While handling, all contact with eyes, skin and clothes should be avoided. Implements used for application should be cleaned with thinner, xylene or toluene.

► Consumption:

PR-100 A, PR-100B 150 g/sq. m for 125 micron thickness

SL-300 A, SL-300B 1. 1 kg/sq. m for 1 mm thickness

► Properties:

Pot Life (25°C) - 25 minutes Touch dry time (25°C) - 4-6 hours

Protecto-Ezeflor PU formulations are subject to strict quality control, innovations and improvements to comply with our high standards. The above information is given on the basis of our best knowledge and information and is for your guidance only. Specifications, however, are subject to change and no guarantee is given or implied. All Rights Reserved.



PRODUCT DEVELOPED & MANUFACTURED BY:
Industrial Products Mfg. Co.

Last Updated: Sept.2012

108/109 Parmar Chambers,
3/4 B. J. Road
Pune 411001 INDIA
Tel: 91-20-26129521, 26122612
Fax: 91-20-26124362
E-mail: Contact@IPMCIndia.com
www.IPMCIndia.com
www.ProtectoCoatings.com